

AMENDMENTS TO THE CLAIMS:

The following is the status of the claims of the above-captioned application, as amended.

Claims 1-17 (Canceled.)

Claim 18. (Currently amended) A coated granule comprising a core and a coating, wherein the core comprises a uniform mixture of a detergent enzyme having an alkaline pH activity optimum, and an acidic buffer component, wherein said acidic buffer component has a pH of 1 to below 7 when measured as a 10 % aqueous solution and a pK_a in the range of 4 to 9 and is selected from the group consisting of phosphates, ~~eitrates~~, citric acid, salts of citric acid, malonic acid, succinic acid, glutaric acid ~~and~~, adipic acid, and disodium hydrogen citrate, wherein at ~~least 25%~~ more than 50% w/w of the core is acidic buffer component.

Claim 19. (Previously presented) The granule according to claim 18, wherein the pH of the acidic buffer component is 3 to below 7.

Claim 20. (Previously presented) The granule according to claim 18, wherein the pK_a of the acidic buffer component is 5 to 7.

Claim 21. (Previously presented) The granule according to claim 18, further comprising an acidic buffer component in the coating.

Claim 22. (Previously presented) The granule according to claim 21, wherein the amount of acidic buffer component present in the core is more than 20 % of the total amount of acidic buffer component present in the granule.

Claim 23. (Previously presented) The granule according to claim 21, wherein the acidic buffer component in the core and in the coating are different.

Claim 24. (Previously presented) The granule according to claim 21, wherein the acidic buffer component in the core has a pH of 4 to below 7 and the acidic buffer component in the coating has a pH of 1 to 5.

Claim 25. (Canceled)

Claim 26. (Currently amended) A granule according to claim 18 comprising at least ~~40~~55% w/w of acidic buffer component in the core.

Claim 27. (Previously presented) The granule according to claim 18, wherein the acidic buffer components are selected from the group consisting of NaH_2PO_4 , KH_2PO_4 , $\text{Ca}(\text{H}_2\text{PO}_4)_2$ and sodium hexametaphosphate or mixtures thereof.

Claim 28. (Previously presented) The granule according to claim 18, wherein the acidic buffer component is Na_2H -citrate.

Claim 29. (Previously presented) A detergent composition comprising a granule of claim 18.

Claim 30. (Currently amended) A process for preparing granules of claim 18 comprising: _____ preparing a core comprising a detergent enzyme having an alkaline pH activity optimum and at least ~~25~~more than 50% w/w of acidic buffer component having a pH of 1 to below 7 when measured as a 10 % aqueous solution and a pK_a in the range of 4 to 9, and _____ coating the core with a coating material.

Claim 31. (Previously presented) The process according to claim 30, wherein the granule is prepared in a mixer, a fluid bed, a fluidized spray dryer, a spray fluidizer, a spray dryer or an extruder.

Claim 32. (Currently amended) A coated granule comprising a core and a coating, wherein the core comprises a uniform mixture of a detergent enzyme having an alkaline pH activity optimum, and an acidic buffer component, wherein said acidic buffer component has a pH of 1 to below 7 when measured as a 10 % aqueous solution and a pK_a in the range of 4 to 9 and is selected from the group consisting of phosphates, ~~citrates~~, citric acid, salts of citric acid, malonic acid, succinic acid, glutaric acid and -adipic acid, and disodium hydrogen citrate, wherein at least ~~40~~55% w/w of the core is acidic buffer component.

Claim 33. (Previously presented) A granule in accordance with claim 32, wherein the pH of the acidic buffer component is 3 to below 7.

Claim 34. (Previously presented) A granule in accordance with claim 32, wherein the pK_a of the acidic buffer component is 5 to 7.

Claim 35. (Previously presented) A granule in accordance with claim 32, further comprising an acidic buffer component in the coating.

Claim 36. (New) A granule in accordance with claim 18, wherein at least 51% w/w of the core is acidic buffer component.

Claim 37. (New) A granule in accordance with claim 18, wherein at least 52% w/w of the core is acidic buffer component.

Claim 38. (New) A granule in accordance with claim 18, wherein at least 54% w/w of the core is acidic buffer component.

Claim 39. (New) A granule in accordance with claim 18, wherein at least 56% w/w of the core is acidic buffer component.